

USSN 10/734,078

IN THE CLAIMS

- 1.-10. (Canceled)
- 11.(currently amended) A coated article, comprising a nickel base superalloy substrate consisting essentially of, in weight %, about 3% to about 12% Cr, up to about 15% Co, up to about 3% Mo, about 3% to about 10% W, up to about 6% Re, about 5% to about 7% Al, up to about 2% Ti, up to about 1% Fe, up to about 2% Nb, about 3% to about 12% Ta, up to about 0.07% C, about 0.030% to about 0.80% Hf, up to about 0.10% Zr, up to about 0.02% B, up to about 0.050% of a rare earth element, and balance Ni and incidental impurities; an outwardly grown, single phase platinum-modified diffusion aluminide bondcoat on the substrate, and a ceramic thermal barrier coating comprising zirconia disposed on the bondcoat wherein spallation life of the ceramic thermal barrier coating during cyclic oxidation is prolonged.
- 12.(original) The article of claim 11 wherein the rare earth element is selected from the group consisting of Y and Lanthanide series elements with atomic numbers from 58 to 71.
- 13.(currently amended) The article of claim 12 wherein about 0.0005% to about 0.050 weight % of ~~said rare earth element~~ Y is present.
- 14.(original) The article of claim 11 having a sulfur concentration of 2 ppm by weight or less.
- 15.(previously presented) The article of claim 11 wherein the Hf concentration of the substrate is from about 0.33% to about 0.80% by weight.

USSN 10/734,078

16.(cancelled).

17.(previously presented) The article of claim 11 wherein the substrate comprises a gas turbine engine blade.